

ULTIMAKER PC

<u>Chemical Name</u>	Polycarbonate
<u>Description</u>	With Ultimaker PC filament, you can print strong and tough parts that retain dimensional stability when subjected to temperatures as high as 110oC. Our PC is engineered to be printed at moderate temperatures compared to other PC filaments and shows minimized warping providing a seamless 3D printing experience.
<u>Key features</u>	High toughness (especially for the non-transparent filament options), resists temperatures and retains form up to 110oC, flame retardant characteristics, dimensionally stable, strong interlayer bonding (especially when using the front door add-on), good bed adhesion (especially when using the Avery stickers). Allows printing of translucent parts with the transparent filament option.
<u>Applications</u>	Lighting, molds, engineering parts, tools, functional prototyping and short run manufacturing.
<u>Non suitable for</u>	Food contact and in-vivo applications.

FILAMENT SPECIFICATIONS

	VALUE	METHOD
<u>Diameter</u>	2.85 ± 0.05 mm	ultra-fast CCS-based, dual-axis diameter gauge
<u>Max. roundness deviation</u>	0.05 mm	ultra-fast CCS-based, dual-axis diameter gauge
<u>Net filament weight</u>	750 g	-

COLOR INFORMATION

PRODUCT NUMBER	COLOR	COLOR CODE
UM9715	PC Transparent	n/a
UM9716	PC Black	RAL 9005
UM9717	PC White	RAL 9003

MECHANICAL PROPERTIES (*)(**)	TYPICAL VALUE	TEST METHOD
<u>Tensile modulus</u>	2307 MPa (t) / 2048 MPa (b/w)	ASTM D638
<u>Tensile stress at yield</u>	-	-
<u>Tensile stress at break</u>	62.7 MPa (t) / 59.7 MPa (b/w)	ASTM D638
<u>Elongation at yield</u>	-	-
<u>Elongation at break</u>	3.15% (t) / 12.24% (b/w)	ASTM D638
<u>Flexural strength</u>	100.4 MPa (t) / 94.1 MPa (b/w)	ASTM D790
<u>Flexural modulus</u>	2477 MPa (t) / 2044 MPa (b/w)	ASTM D790
<u>Izod impact strength, notched (at 23°C)</u>	-	-
<u>Izod impact strength, unnotched (at 23°C)</u>	-	-
<u>Charpy impact strength, notched (at 23°C)</u>	3.41 kJ/m ² (t) / 25.1 kJ/m ² (b/w)	ASTM D256
<u>Hardness</u>	-	-
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
<u>Melt mass-flow rate (MFR)</u>	32 - 35 g/10 min (t) / 23 - 26 g/10 min (b/w)	(300 °C, 1.2 kg)
<u>Heat deflection (HDT) at 0.455 MPa</u>	-	-
<u>Heat deflection (HDT) at 1.82 MPa</u>	-	-
<u>Glass transition</u>	112 - 113 °C	DSC, 10 °C/min
<u>Coefficient of thermal expansion (flow)</u>	-	-
<u>Coefficient of thermal expansion (xflow)</u>	-	-
<u>Melting temperature</u>	-	-
<u>Thermal shrinkage (hot air, 100 °C, 30 min)</u>	-	-
OTHER PROPERTIES	TYPICAL VALUE	TEST METHOD
<u>Specific gravity</u>	1.18 - 1.20	ASTM D792
<u>Flame classification</u>	-	-

(*) On 3D printed bars, see notes.

(**) t: transparent. b/w: black/white.

NOTES

Properties reported here are average of a typical batch. The mechanical properties are from specimens printed flat at 100% infill under 45°, 2 shells, 0% fan speed, middle of the bed, nozzle temperature 255 °C, bed temperature 80 °C, BuildTak sheet on the bed, nozzle diameter 0.4 mm, all print speeds are 60 mm/s, and layer height 0.2 mm

DISCLAIMER

Any technical information or assistance provided herein is given and accepted at your own risk, and neither Ultimaker nor its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made regarding the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale.

VERSION

Version 2.001

DATE

09/08/2016